

izomaks  
أيزوماكس

[www.izomaks.com.sa](http://www.izomaks.com.sa)

البيتومين السائل  
LIQUID BITUMEN

COLD APPLIED FAST DRYING PRIMER FOR GENERAL PURPOSES ASTM OXIDIZED BITUMEN 115/15

	PROPERTIES	TEST METHOD	MIN	MAX
1	Flash point (tag open cup) °C	ASTM D3143	280	330
2	Density Kg/Ltr at 25 °C	ASTM D-70	1.0	1.1
3	Bitumen softening point °C	ASTM D36	110	115
4	Penetration °C	ASTM D5	12	15
5	Loss on heating for 5 hr at 163 °C mass%	ASTM D1754	-	0.2
6	Solubility in trichloroethylene %	ASTM D2042	99.5	-
7	water, volume %	ASTM D-95	NIL	-

NOTE : THE ABOVE SHOWN TECHNICAL DATA ARE RESULTS OBTAINED IN LABORATORY AND EXTRA DETAILS CAN BE PROVIDED UPON REQUEST. IN ACCORDANCE TO ASTM AND UEA'S STANDARDS RESULTS ARE SUBJECTED TO A VARIATION OF 20 % .



**izomaks**  
OXIDIZED

صنعت البترول  
MADE IN KSA