

POLYSTAR - 1600

SR	PROPERTIES	UNIT	VALUE	TEST METHOD
1	Softening point	°C	155	ASTM D38
2	Penetration	dmm	15-20	ASTM D 5
3	Cold Flexibility	°C	-2 to -5	ASTM D 5147
4	Heat Resistance (@120 °C for 2h : 15 min)	Pass	No flow	ASTM D 5147
5	Tensile strength @23 + 2 °C			
	Longitudinal	N/5 cm	600	ASTM D 5147
	Transversal		450	
6	Elongation @23 + 2 °C	%		ASTM D 5147
	Longitudinal		40	
	Transversal		45	
7	Lap joint Strength	N/5 cm		UEAtc M.O.A.T 30
	Longitudinal		600	
	Transversal		450	
8	Tear Strength	N		ASTM D 5147
	Longitudinal		400	
	Transversal		300	
9	Puncture Resistance	N	700	ASTM E 154
	Static		L3	UEAtc 5.1.9
	Dynamic		I3	UEAtc 4.4.1
10	Dimensional Stability	%		
	Longitudinal		> 0.6	ASTMD 5147
	Transversal		> 0.6	
11	Resistance to Aging (after 2000 hrs)		No deterioration	ASTM D 4789
12	Water Absorption (@ 25°C for 24 hrs)	%	< 1	ASTM D 5147
13	Water Vapour Transmission,	g/m ² /24hrs	< 0.5	ASTM E 98
14	Resistance to leakage at joints		pass	UEAtc

NOTE : THE ABOVE SHOWN TECHNICAL DATA ARE RESULTS OBTAINED IN LABORATORY AND EXTRA DETAILS CAN BE PROVIDED UPON REQUEST. IN ACCORDANCE TO ASTM AND UEAtc STANDARDS RESULTS ARE SUBJECTED TO A VARIATION OF 20 % .



izomaks
POLYSTAR - 1600

P3000 P4000 P6000 P8000